

# CPD<sup>®</sup> PAVER AND CONCRETE SEALER

## DESCRIPTION

CPD<sup>®</sup> Paver and Concrete Sealer is a clear solvent base methacrylate copolymer resin sealer for interlocking pavers and concrete and is available in gloss, flat and anti-slip finishes.

## WHERE TO USE

This product can be used as a sealer for interlocking pavers on sidewalks and driveways; and on horizontal and vertical exterior concrete surfaces. It can also be used as a sealer on Flagstone and Natural Stone.

## BENEFITS

- gives paver a color enhancing wet look (gloss finish)
- protects against penetration of moisture, deicing salts, rust, oil and grease
- will not yellow on exterior exposure
- available in gloss, flat and anti-slip finishes

## PREPARATION

The ideal surface is a new surface. CPD<sup>®</sup> Paver and Concrete Sealer should be applied directly after the paving stones are installed and cleaned and allowed to dry completely or the concrete surface is dry. Previously installed paving stones or existing concrete surfaces must be clean and dry, free from all grease, oil, laitence and other foreign matter. If doubt exists as to the condition of the surface, chemical cleaning is recommended. Under no conditions should paving stones or concrete surfaces be cleaned by sand blasting. Contact a CPD<sup>®</sup> Technical Representative for a cleaning recommendation if doubt exists as to the condition of the concrete surface.

Interlocking pavers must be cleaned of all efflorescence using a dilute solution (6-8 to 1) of Sure Klean<sup>®</sup> #600 Detergent. Apply as per directions. Thoroughly rinse and allow to dry completely prior to application of CPD<sup>®</sup> Paver and Concrete Sealer. Interlocking pavers that have been cleaned using high water pressure will require a longer drying time due to the amount of moisture forced in and around the pavers. Application of CPD<sup>®</sup> Paver and Concrete Sealer before pavers are dry will entrap moisture and turn the surface white.

## APPLICATION

CPD<sup>®</sup> Paver and Concrete Sealer may be applied by roller, brush or sprayer depending on surface texture. If spraying, hold nozzle close to surface so as not to atomize the solvent carrier, especially in hot weather. One coat is recommended; however if a second coat is applied, it should be applied after 24 hours in the opposite direction. At 21°C (70°F) CPD<sup>®</sup> Paver and Concrete Sealer will dry tack free in approximately 30 minutes. Do not apply sealer when the substrate is in direct sunlight. Allow to cure for a minimum:  
12 hours @ 23°C (74°F) for foot traffic  
24 hours @ 23°C (74°F) for vehicle traffic

## LIMITATIONS

- do not apply to damp or wet surfaces
- do not apply below 5°C (40°F)
- protect from rain until dry

## COVERAGE

5-7 m<sup>2</sup>/L per Coat (200-280 ft<sup>2</sup>/U.S. gal) depending on porosity and surface texture.

## STANDARDS

Approved by the Ministry of Transportation of Ontario (MTO) for use on vertical concrete surfaces (Test M1-127).

## PACKAGING

208L drum (55 US gal)/ 210 kg (462 lb)  
18.9L pail (5 US gal)/ 18 kg (39.6 lb)  
3.79L can (1 US gal) (4 per case)/ 16 kg (35.2 lb) per case

## CLEAN UP

Clean equipment with CPD<sup>®</sup> Xylol immediately after application. CAUTION: CPD<sup>®</sup> Xylol is a flammable solvent. Review M.S.D.S. prior to using.

## STORAGE

Store in a dry location. Freezing will not affect product but temperature of product before use must be 15°C (60°F) minimum.

## TRANSPORTATION REGULATION

Regulated Dangerous Good. Flammable Liquid: (Xylene) Class 3/9.2) UN 1307 PG III.

07190-50-0810

### **SAFETY PRECAUTIONS**

Flammable liquid. Consult Material Safety Data Sheet (M.S.D.S.) for specific instructions. MSDS # 2.

### **SHELF-LIFE**

Two years from date of manufacture when stored in original unopened containers.

### **WARRANTY**

The recommendations made and the information herein is based on our own and independent laboratory experience, and is believed to be accurate under controlled conditions. However, no warranty or guarantee of accuracy is made because we cannot cover every possible application of product nor anticipate every variation encountered in weather conditions, job-conditions, methods used and types of surfaces on which the product is applied. The users shall make their own tests to determine the suitability of such products for any particular purpose.

CPD<sup>®</sup> makes no warranties with respect to this product, expressed or implied, without limitation, the implied warranties of merchantability or fitness for a particular purpose.

CPD<sup>®</sup>'s liability shall be limited in all events to supplying sufficient product to re-treat and/or repair the specific area to which CPD<sup>®</sup> product has been applied. CPD<sup>®</sup> reserves the right to have the true cause of any difficulty determined by accepted test methods. CPD<sup>®</sup> shall have no other liability, including liability for incidental, consequential or resultant damages, however caused, whether due to breach of warranty, negligence, or strict liability.

THIS WARRANTY MAY NOT BE MODIFIED OR EXTENDED BY REPRESENTATIVES OF CPD<sup>®</sup>, ITS DISTRIBUTORS OR DEALERS.